

Storage of Compressed fibre jointing sheets

Recommended conditions:

- Dry and dark warehouse
- Storage temperature from -10°C to +25°C, at higher temperatures hardening of sealing sheets risks
- Relative humidity 50-60%
- Do not store Sealants near sources of radiant heat (radiators, hot water pipes, hot water units)
- Avoid direct sunlight, UV radiation can cause embrittlement of sealing sheets
- Store in a horizontal position on a firm ground and in the original packaging

Recommended storage time:

When those conditions are met, the storage period is 2 years.



Temac, a.s.
Zvěřinec 289 13
Czech Republic
Gasket and sealing technology

Telephone: +420 325 550 181
Fax: +420 325 550 250
e-mail: tech.help@temac.cz
www.temac.cz